Product Description

Total Thickness:	1.83 mils (nominal)
Adhesive:	Synthetic Rubber Hot Melt
Color(s):	Clear

Physical Properties

Tensile Strength (lbs/in):	26	PSTC-131*	(ASTM D3759**)
Elongation (% at break):	165	PSTC-131	(ASTM D3759)
180° Peel Adhesion (oz/in):	47	PSTC-101	(ASTM D3330***)
Resistance to UV Lighting:		Fair	

Application Temperature

50° to 110° F

Operation Temperature

30° to 140° F

Typical Applications

For sealing moderate weight cartons subjected to normal shipping conditions in a wide range of temperatures where quick tack, fast production hot melt adhesive is desired.

Other Standards and Specifications

Complies with environmental considerations of ASTM D 1974-14

Application and Operating Conditions:

*Pressure Sensitive Tape Council
**ASTM Standard D3759, “Standard Test Method for Tensile Strength and Elongation of Pressure Sensitive Tapes”
***ASTM Standard D3330, “Standard Test Method for Peel Adhesion of Pressure Sensitive Tapes”

75 Industrial Park Drive, Rogersville, TN 37857
(800) 235-8273/(714) 249-1488 Fax (800) 235-8273/(714)
STA, LLC www.sta-tapes.com