

## Description

Backing:	3-way reinforcing yarns laminated between 2 sheets of 20# and 23# kraft paper with a non-asphaltic, water-resistant, flexible, and non-staining amorphous polyolefin based adhesive. Glass fibers in the machine direction average no more than 5/8" apart. Glass fibers in the cross direction are arranged in a diamond pattern with the spacing between the parallel sides of the diamond averaging not more than 1 1/4".
Adhesive:	Non-toxic and odorless synthetic starch
Color:	Natural or white

## Physical Properties

Tensile Strength (lbs/in) Machine Direction:	40-45	PSTC-131*	(ASTM D-828)
Tensile Strength (lbs/in) Cross Direction:	22-27	PSTC-131	(ASTM D-828)
Elongation (% at break):	NR	PSTC-131	(ASTM D3759)

## Application &amp; Operating Conditions:

The conditions at which the tape is unwound and applied to the substrate. Under normal conditions, the tape should unwind and adhere to the substrate properly and perform as normally expected. The tape should be used within 1 year of the date of shipment.

## Notes:

The information listed above has been obtained from controlled laboratory tests and is reliable, but should not be used for the purpose for writing specifications. It is offered in good faith, but without guarantee, as conditions and methods of use of our products and beyond our control. It is recommended that the prospective user determine their suitability before adopting them on a commercial scale.

\*Pressure Sensitive Tape Council

\*\*ASTM International, West Conshohocken, PA. DOI: 10.1520/D3759 -D3759M-10, [www.astm.org](http://www.astm.org)